MOTIP Carat Primer

Información técnica



Fast drying primer to treat surfaces, treated and untreated, of wood, metal, aluminium, glass and stone. Suitable primer as pre treatment for re-spraying with all lacquer systems (alkyd resin, nitro cellulose, 1-K acrylic and 2-K acrylic lacquers). The primer has excellent coverage and filling properties and is corrosion preventive. Carat Primer has excellent vertical stability so hardly any dripping and is easy to sand, both wet and dry (from grain 400).

Ord.-no.: 08106, 08108

Calidad y propiedades

Fast drying
Excellent coverage and filling properties
Corrosion preventive
Excellent vertical stability so hardly any dripping
Easy to sand, both wet and dry (from grain 400)
Re-sprayable with all lacquer systems

Datos físicos y químicos

Base: Acrylic resin
Nombre del color:
- White
- Grey

Grado de brillo: mat, 10 ±2
Eficacia: 400 ML – 1,25 - 1,75 m²
Polvo seco: 5 - 10 min
Seco al tacto: 10 - 20 min
Completamente seco: 120 min
Sobrecubierta: 120 min
Superfici: wood, metal, aluminium, glass, stone and various types of plastic.
Temperatura mínima de trabajo: 15 °C
Temperatura máxima de trabajo: 25 °C
Punto de inflamación: n.a.
Resistencia térmica: 110 °C
Contenido:
- 400 ML
- 400 ml

European Aerosols GmbH, Kurt-Vogelsang-Straße 6, 74855 Haßmersheim – info-de@european-aerosols.com
European Aerosols B.V., Wolfraamweg 2, NL-8471 XC Wolvega – info-nl@european-aerosols.com

Cómo utilizarlo

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.
The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.
Apply the primer in several thin layers. Before applying the next layer, again shake the aerosol.
After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).
The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

Respetuoso con el medio ambiente

European Aerosols se compromete a aplicar formulaciones sin ingredientes restringidos o críticos y a conseguir el mejor rendimiento posible. Los tapones y envases están fabricados con material reciclable.

Eliminación

Sólo las latas completamente vacías deben depositarse en el contenedor de reciclaje o en el contenedor adecuado para residuos recuperables. Las latas que no estén vacías deben eliminarse como «basura especial».

Marcado/Etiquetado

Todos los productos fabricados por European Aerosols cumplen la normativa de etiquetado vigente según la directriz de preparación 1999/45/EG. Todos los aerosoles cumplen las normas TRGS 200 y TRG 300, así como la directriz sobre aerosoles 75/324/EWG en su versión vigente.

Fecha de publicación: 5 agosto 2025 – Esta versión sustituye a todas las anteriores.

European Aerosols GmbH, Kurt-Vogelsang-Straße 6, 74855 Haßmersheim – info-de@european-aerosols.com
European Aerosols B.V., Wolfraamweg 2, NL-8471 XC Wolvega – info-nl@european-aerosols.com